






# Gold סרט איטום KOBauflex 315PP



## Application range / properties

**Kobauflex® 315 PP** is intended for the permanent sealing of construction joints, connecting joints and cracks, in particular for objects with normal and reduced stress in residential buildings. Preferred applications are e.g. kitchens, showers and bathrooms. **Kobauflex® 315 PP** is tearproof and durable. Due to the basic elastomer EPDM (black) it is characterized by very good chemical resistance, balanced mechanical qualities and excellent ozone and ageing resistance.

## Handling

The base has to be capable of bearing the load, as dry as possible and free of dust, dirt as well as other components reducing adhesion and loose particles. Chipped spots on edges have to be profiled using appropriate repair systems. Gravel nests and unevenness are to be filled. Separating components, such as cement paste, loose coatings as well as angular grain in the surface are to be removed by means of appropriate measures (e.g. sandblasting, knocking off).

Mix the adhesive or mortar provided for the sealing measure in each case according to the manufacturer's instructions observing, if required, maturing periods. Then apply the ready mix by means of a flat bristle brush or radiator brush to the base until saturation. Observe the processing times and/or pot life of the adhesive or mortar! Subsequently place **Kobauflex® 315 PP** joint sealing tape from the roll wrinkle-free on the wet adhesive bed and press the edge of the substrate on the surface using a spatula or smoothing trowel so that the adhesive/mortar completely penetrates the substrate. For the corner areas, use **Kobauflex®** sealing corners inside / outside and for pipe penetrations Dichtflex sealing sleeves. Subsequently, apply adhesive/mortar wet in wet as finishing coat until the area of the substrate is completely covered.

## Technical data

### Tape design

Material layer:	PP non-woven 50 g
Material lamination:	PP non-woven 30 g
Width sealing zone:	approx. 70 – 100 mm
Width elongation zone:	approx. 20 mm
Total width:	approx. 120 – 150 mm

### Data sheet elastomer

Polymer sealing zone:	EPDM
Colour:	black
Hardness [DIN 53 519 Teil 2]:	55° Sh ± 5°
Tensile strength [DIN 53 504]:	9 N/mm <sup>2</sup>
Elongation at break [DIN 53 504]:	400 %
Compression set 22h/70°C [VDA 675 217]:	25%
Tear growth resistance [VDA 675 211A]:	7 N/mm
Ozone resistance [DIN 53 309]:	resistant
Temperature range:	-40°C to + 100°C

## Form of delivery

Length of roll on request

## Tools / embedding materials

- Flat bristle brush, brush, spatula, smoothing trowel
- Embedding material according to the manufacturer, roughness of the base and method

## Storage

At dry, cold and closed places

## Note

Protect **Kobauflex® 315 PP**.Objektdichtband EPDM (black) from mechanical damage during the building activities. Further work is to be performed as instructed by manufacturer.