





ISRANOVA-R APP 5

DESCRIPTION

ISRANOVA-R APP 5 is a plastomeric modified bitumen waterproofing membrane (APP), industrially manufactured by impregnation of the nonwoven spunbond polyester reinforcement with the waterproofing compound based on distilled bitumen modified with polyolefin polymers, which gives to the compound superior technical characteristics.

Shaping of sheets, straightness, dimensional and surface uniformity are accomplished by hot calendering of the mass at hot melt fluid state.

The upper surface is coated with anti-adhesive amorphous sand. The lower surface is coated with a thermo-fusibile polyolefin film.

FIELD OF APPLICATION

ISRANOVA-R APP 5 is particularly suitable as principal layer in multi-layer waterproofing systems, with compatible membranes.

General roofing, vehicles parking roofs, foundations, on or under floors or ground slabs, wall constructions, are valid examples of the design application of this product. It is not suitable for roof gardens. It can be applied onto every substrate (concrete, masonry, steel, wood, insulation panel, membrane, etc.) and under heavy protection.

The excellent mechanical characteristics and high level thermo-dynamic stability make it suitable for any climate conditions and all the situations where a barrier against water is required.

METHOD OF INSTALLATION

The excellent thermoplastic properties of the waterproofing compound allow the application with torchon system or hot air generator. In particular situations, it could be applied with appropriate sealants or mechanical fastenings.

The application of the membrane must be carried in good weather conditions and after the substrate has been adequately cleaned and prepared.

PACKING AND STORAGE

The product is packed as standing rolls on wooden pallets wrapped with thermoshrinking protective hoods. Rolls must be stored in the upright position, without stacking the pallets to avoid deformations which can compromise the correct application of the membrane. The product must be stored indoor, protected from heat and frost.

The product does not contain dangerous substances and can be considered as household rubbish or industrial waste (identification code EWC170302).

INTENDED USE OR USES

Flexible sheets for waterproofing. Reinforced bitumen sheets for roof waterproofing


Concrete bridge decks and other trafficked areas of concrete EN13707:2013

EN13969:2004 /A1:2006

Flexible sheets for waterproofing. Bitumen damp proof sheets including bitumen basement tanking sheets

Roofing sheets: Modified bitumen sheets reinforced with non-woven polyester or other fibers for use by welding

- 1. Anti-adhesive surface
- 2. Waterproofing mass
- 3. Reinforcement
- 4. Waterproofing mass
- 5. Torch-off film











ISRANOVA-R APP 5

Rev. 1 del 01/07/2013



TECHNICAL DATA

Thickness of bitumen above reinforcement layer EN1849-1:1999 5 (mm) ≥ Thickness of bitumen above reinforcement layer EN13897:2004 1,0 ≥ Thickness of bitumen below reinforcement layer EN13897:2004 1,5 ≥ Roll length EN1848-1:1999 7,5 (m) >=99% Roll width EN1848-1:1999 0 - 20 mm / 10 m Straightness EN1848-1:1999 0 - 20 mm / 10 m Flexibility at low temperature (pliability) EN1109:2013 -10 (°C) ≤ Heat flow resistance EN1110:2010 135 (°C) ≥ Water vapour transmission properties EN1931:2000 20 .000 (µ) - Water vapour transmission properties EN12311-1:1999 600 / 500 (N/50 mm) >= Tensile properties: maximum tensile strength EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12311-1:1999 30 / 130 (N) >= Resistance to tearing (nail shank) EN12310-1:1999 500 / 500		Norm	Value	Unit	Tolerance
Thickness of bitumen below reinforcement layer EN13897:2004 1,5 ≥ Roll length EN1848-1:1999 7,5 (m) >=99% Roll width EN1848-1:1999 1 (m) >=99% Straightness EN1848-1:1999 0 - 20 mm / 10 m Flexibility at low temperature (pliability) EN1109:2013 -10 (°C) ≤ Heat flow resistance EN1110:2010 135 (°C) ≥ Water vapour transmission properties EN1931:2000 20.000 (μ) Tensile properties: maximum tensile strength EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12317-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 35 / 35 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12370-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 PASSED Ageing 30 days at 80 °C EN13948:2007 PASSED -	Thickness	EN1849-1:1999	5	(mm)	≥
Roll length EN1848-1:1999 7,5 (m) >=99% Roll width EN1848-1:1999 1 (m) >=99% Straightness EN1848-1:1999 0 - 20 mm / 10 m Flexibility at low temperature (pliability) EN1109:2013 -10 (°C) ≤ Heat flow resistance EN1110:2010 135 (°C) ≥ Water vapour transmission properties EN1931:2000 20.000 (μ) - Water vapour transmission properties EN1931:2000 20.000 (μ) - Tensile properties: maximum tensile strength EN12311-1:1999 600 / 500 (N/50 mm) >= Tensile properties: elongation at break EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12310-1:1999 30 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12370-A:2015 250 (kg)	Thickness of bitumen above reinforcement layer	EN13897:2004	1,0		≥
Roll width EN1848-1:1999 1 (m) >=99% Straightness EN1848-1:1999 0 - 20 mm / 10 m Flexibility at low temperature (pliability) EN1109:2013 -10 (°C) ≤ Heat flow resistance EN1110:2010 135 (°C) ≥ Water vapour transmission properties EN1931:2000 20.000 (μ) - Tensile properties: maximum tensile strength EN12311-1:1999 600 / 500 (N/50 mm)>= Tensile properties: elongation at break EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12310-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 5	Thickness of bitumen below reinforcement layer	EN13897:2004	1,5		2
Straightness EN1848-1:1999 0 - 20 mm / 10 m Flexibility at low temperature (pliability) EN1109:2013 -10 (°C) ≤ Heat flow resistance EN1110:2010 135 (°C) ≤ Water vapour transmission properties EN1931:2000 20.000 (µ) - Tensile properties: maximum tensile strength EN12311-1:1999 600 / 500 (N/50 mm) >= Tensile properties: elongation at break EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12310-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12370-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN1925-2:2010/EN13501-1:2007+A1:2009	Roll length	EN1848-1:1999	7,5	(m)	>=99%
Flexibility at low temperature (pliability) EN1109:2013	Roll width	EN1848-1:1999	1	(m)	>=99%
Heat flow resistance EN1110:2010 135 (°C) ≥ Water vapour transmission properties EN1931:2000 20.000 (μ) - M.d. C.d. Tensile properties: maximum tensile strength EN12311-1:1999 600 / 500 (N/50 mm) >= Tensile properties: elongation at break EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12310-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance of joints (mixture) EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance of joints to leakage EN12307-2:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:	Straightness	EN1848-1:1999	0	-	20 mm / 10 m
Water vapour transmission properties EN1931:2000 20.000 (μ) - M.d. C.d. Tensile properties: maximum tensile strength EN12311-1:1999 600 / 500 (N/50 mm) >= Tensile properties: elongation at break EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12310-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12317-1:1999 500 / 500 (N/50 mm) >= Water penetration under hydraulic pressure EN13897:20015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - External fire performance EN1187:2012/EN13501-1:2007+A1:2009 F Class - Resist	Flexibility at low temperature (pliablility)	EN1109:2013	-10	(°C)	≤
M.d. C.d. Tensile properties: maximum tensile strength EN12311-1:1999 600 / 500 (N/50 mm) >= Tensile properties: elongation at break EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12310-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12730-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - Ageing 30 days at 80 °C EN13948:2007 PASSED -	Heat flow resistance	EN1110:2010	135	(°C)	≥
Tensile properties: maximum tensile strength EN12311-1:1999 600 / 500 (N/50 mm) >= Tensile properties: elongation at break EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12310-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12370-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - Ageing 30 days at 80 °C EN13948:2007 PASSED -	Water vapour transmission properties	EN1931:2000	20.000	(µ)	-
Tensile properties: elongation at break EN12311-1:1999 35 / 35 (%) >= Resistance to tearing (nail shank) EN12310-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12730-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - - Ageing 30 days at 80 °C EN13948:2007 PASSED - - -			M.d. C.d.		
Resistance to tearing (nail shank) EN12310-1:1999 130 / 130 (N) >= Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12730-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - - Ageing 30 days at 80 °C EN13948:2007 PASSED - - -	Tensile properties: maximum tensile strength	EN12311-1:1999	600 / 500	(N/50 m	m) >=
Dimensional stability EN1107-1:1999 ±0,5 / ±0,5 (%) ≤ Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12730-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - - - Ageing 30 days at 80 °C EN13948:2007 PASSED - - - -	Tensile properties: elongation at break	EN12311-1:1999	35 / 35	(%)	>=
Shear resistance of joints EN12317-1:1999 500 / 500 (N/50 mm) >= Resistance to static puncture EN12730-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - Ageing 30 days at 80 °C EN13948:2007 PASSED -	Resistance to tearing (nail shank)	EN12310-1:1999	130 / 130	(N)	>=
Resistance to static puncture EN12730-A:2015 250 (kg) ≥ Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - - Ageing 30 days at 80 °C EN13948:2007 PASSED - - -	Dimensional stability	EN1107-1:1999	±0,5 / ±0,5	(%)	≤
Water penetration under hydraulic pressure EN13897:2004 2 ≥ Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - - Ageing 30 days at 80 °C EN13948:2007 PASSED - -	Shear resistance of joints	EN12317-1:1999	500 / 500	(N/50 m	m) >=
Resistance of joints to leakage EN13897:2004 10 ≥ External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - - Ageing 30 days at 80 °C EN13948:2007 PASSED - -	Resistance to static puncture	EN12730-A:2015	250	(kg)	2
External fire performance EN1187:2012/EN13501-5:2005+A1:2009 Froof Class - Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD - - Visible defects EN1850-1:2001 PASSED - - Ageing 30 days at 80 °C EN13948:2007 PASSED - -	Water penetration under hydraulic pressure	EN13897:2004	2		2
Reaction to fire EN11925-2:2010/EN13501-1:2007+A1:2009 F Class - Root resistance EN13948:2007 NPD - - Visible defects EN1850-1:2001 PASSED - - Ageing 30 days at 80 °C EN13948:2007 PASSED - -	Resistance of joints to leakage	EN13897:2004	10		2
Root resistance EN13948:2007 NPD Visible defects EN1850-1:2001 PASSED - - - Ageing 30 days at 80 °C EN13948:2007 PASSED - - -	External fire performance	EN1187:2012/EN13501-5:2005+A1:2009	Froof	Class	-
Visible defects EN1850-1:2001 PASSED - - Ageing 30 days at 80 °C EN13948:2007 PASSED - -	Reaction to fire	EN11925-2:2010/EN13501-1:2007+A1:20	09 F	Class	-
Ageing 30 days at 80 °C EN13948:2007 PASSED	Root resistance	EN13948:2007	NPD		
	Visible defects	EN1850-1:2001	PASSED	-	-
Ageing due Q.U.V. test EN1297:2004 PASSED	Ageing 30 days at 80 °C	EN13948:2007	PASSED	-	-
	Ageing due Q.U.V. test	EN1297:2004	PASSED	-	-

NORMS AND CERTIFICATIONS

EN13707; EN13969 - 1381 - 1381-CPR-415; IS1430 p.3 - 18487





Damp proof courses

Top layer

